

# Paraffin dipping wax



## Technical Data Sheet

Product description: Dipping wax for the coating of ear impressions

Manufacturer: Dreve Otoplastik GmbH  
Max-Planck-Straße 31  
59423 Unna / Germany

Composition:

Pos	chemical term
1	mixture of paraffinic hydrocarbon
2	anti-oxidant

Colour: white

Form: solid

Liquid density: 0.774 g/cm<sup>3</sup> at 80 °C (according to DIN 51757)

Kinematic viscosity: about 4.5 mm<sup>2</sup>/s at 100 °C (according to DIN 51562)

Flash point: > 100 °C (according to DIN/ISO 2592)

Solidification temperature: about 59 °C (according to DIN/ISO 2207)

Proceeding: Melt wax in a wax dip unit and keep at a working temperature of about 75 °C

Dreve Otoplastik GmbH

Max-Planck-Str. 31

59423 Unna / Germany

Tel.: 02303 / 8807-0

Fax: 02303 / 82909

info@dreve.de

www.dreve.com