

# Fotogel



## Technical Data Sheet

Product description: Forming gel on the basis of Agar-Agar for the light-polymerisation

Manufacturer: Dreve Otoplastik GmbH  
Max-Planck-Straße 31  
59423 Unna / Germany

Composition:

Pos	chemical term
1	Glycerine / Water mixture
2	Agar-Agar
3	Additives
4	Preserving agent

Colour: clear, slightly cloudy

Form: solid at 23 °C

Solidification temperature: 42 °C ± 2 °C

Melting temperature: 92 °C ± 2 °C

Density: 1.1 g/cm<sup>3</sup> - 1.2 g/cm<sup>3</sup> at 20 °C

Viscosity: 0.8 Pa s ± 0.3 Pa s at 55 °C

pH-value: 7.0 ± 0.3 at 20 °C

Dreve Otoplastik GmbH  
Max-Planck-Str. 31  
59423 Unna / Germany  
Tel.: 02303 / 8807-0  
Fax: 02303 / 82909  
info@dreve.de  
www.dreve.com